# 360000013



## ConQuest® Empty Conduit, 12.7 mm, black

 \*Product complies with the Build America, Buy America Act (BABAA) requirements of the Infrastructure Investment and Jobs Act of 2021 (Pub. L. 117- 58, §§ 70901-70953), or is the subject of a waiver approved by the Secretary of Commerce or designee. Compliance requirements and waiver applicability vary based on government funding program. Check the laws and regulations for your specific program.

#### **Product Classification**

Regional AvailabilityNorth AmericaProduct TypeEmpty conduitProduct BrandConQuest®

**Government Funding**Build America Buy America (BABA) compliant\*

### General Specifications

**Color** Black

Conduit Type Non-toneable

Density Test Method ASTM D792A

 Density, maximum
 0.955 g/cm³ | 0.035 lb/in³

 Density, minimum
 0.941 g/cm³ | 0.034 lb/in³

**Design Standard** ASTM D3350-05

Wall Type Smooth

#### **Dimensions**

**Inner Diameter, nominal** 10.008 mm | 0.394 in

Outer Diameter, nominal 12.7 mm | 0.5 in

Wall Thickness, minimum 1.346 mm | 0.053 in

Nominal Size 12.7 mm

## Material Specifications

Flexural Modulus, minimum 551.581 N/mm<sup>2</sup> | 80000 psi

Flexural Property Test Method ASTM D790

**Hydrostatic Design Basis**Not pressure rated

**Hydrostatic Design Test Method**ASTM D2837

COMMSCOPE®

# 360000013

Material Type High density polyethylene (HDPE)

Melt Flow Rate Test MethodASTM D1238Melt Flow Rate, maximum0.39 g/10 min

Mechanical Specifications

Minimum Bend Radius, unsupported 152.4 mm | 6 in

Tensile Property Test Method ASTM D638

**Tensile Strength at yield, minimum** 20.684 N/mm<sup>2</sup> | 3000 psi

**Pulling Tension, maximum** 86.183 kg | 190 lb

**Environmental Specifications** 

**Environmental Stress Crack Resistance** Failure rate of 10% within 96 hours

**Environmental Stress Test Method** ASTM D1693, ESCR Condition B

Packaging and Weights

**Weight, net** 46.133 kg/km | 31 lb/kft

Regulatory Compliance/Certifications

Agency Classification

ISO 9001:2015 Designed, manufactured and/or distributed under this quality management system



### \* Footnotes

**Environmental Stress Crack Resistance** ESCR—Environmental Stress Crack Resistence

